

**TD.465 – TECHNICAL DATA: E100-UL7™ Underlayment Epoxy**

Revised: 11/26/19

**Product Name:** E100-UL7™ Underlayment Epoxy – 100% Solids Epoxy

**Product Class:** A high-build or thin, underlayment epoxy floor coating for commercial and industrial use.

**Description:** E100-UL7™ underlayment epoxy is 100% solids, USDA acceptable clear epoxy resin designed for use as an inexpensive base coat for broadcast flooring, sealing concrete, binder for epoxy mortars, crack repair adhesive. Convenient mix ratio of 2 to 1 (A to B). Available in clear only but can be pigmented in the field with special powdered or liquid pigment.

**Uses:**

- Base coat broadcasts
- Sealing cracks in concrete
- Binder for epoxy mortars and slurry coats
- Sealing and protecting concrete

**Features:**

- High strength
- Bonds to dry or slightly damp concrete
- High strength
- Low Viscosity

**Physical Properties:**

Property	Test Standard	Result
Mix Ratio:		2 to 1 by volume
Gel Time:	ASTM C-881	24 minutes
Color (mixed)		Clear
Consistency		Flowable
Compressive Strength	ASTM D-695	12,000 psi
Compressive Modulus	ASTM D-695	>380,000 psi
Absorption	ASTM D-570	0.15%
Heat Deflection Temperature	ASTM D-638	135 F
Elongation @ break	ASTM D-638	3.5%
Viscosity		
Part A Resin		900 cps
Part B Hardener		400 cps
Mixed		700 cps

**Mix Ratio:**

2 parts A to 1 Part B by volume

**Cure Schedule:** 73°F (23°C)

- Pot Life: 24 minutes (200gm Mass)
- Recoat: 12 hours
- Foot traffic: 14 hours
- Full cure: 16 hours
- Water spot resistance: 48 hours

**Available in:**

- 3 gal. kits
- 15 gal. kits
- 150 gal. kits